

AMENDMENTS TO THE CLAIMS

1. (Currently amended) A process of producing a polyester-based polymer, characterized by comprising continuously feeding a polymer (A) having hydroxyl groups and/or ester linkages and one or more species of cyclic esters (B) into a reactor comprising a ~~column-type~~column-shaped agitating mixer having two or more shafts of agitation and a static mixer connected to an outlet thereof and then subjecting them to ring opening polymerization, to obtain a copolymer (C)

wherein the agitating mixer has (i) a combination of a screw paddle and a kneading disk paddle, (ii) a combination of kneading disk paddles, (iii) glass blades or (iv) lattice blades.

2. (Original) A producing process according to claim 1, wherein the polymer (A) is a crystalline aromatic polyester.

3. (Currently amended) A producing process according to ~~claim 1 or 2~~claim 1, wherein the cyclic ester (B) is a lactone.

4. (Original) A producing process according to claim 3, wherein the lactone is ϵ -caprolactone.

5. (Currently amended) A producing process according to any of claims 1 to 4, wherein the conversion of reaction of the cyclic ester (B), is 75 mole % or less after passing through the ~~column-type~~column-shaped agitating mixer having two or more shafts of agitation and before passing through the static mixer, and it is 75 mole % or more after passing through the static mixer.

6. (Currently amended) A process of continuously producing a polyester-based polymer, characterized by continuously feeding a polymer (A) having hydroxyl groups and/or ester linkages and one or more species of cyclic esters (B) into a continuous reactor having a static

mixer and then subjecting them to ring opening polymerization to obtain a copolymer (c) in which:

the continuous reactor, whose mixer(s) consists essentially of a static mixer, at least comprises a static mixer (SM(i)) for use in an early stage of reaction and a static mixer (SM(e)) for use in a final stage of reaction, the static mixer (SM(e)) being connected to SM(i) in series and being a type different from that of SM(i);

the X (i:e) value is 4 or greater, the value being calculated by substituting the pressure loss ratios Zi of SM(i) and Ze of SM(e) and the inside diameters Di of SM(i) and De of SM(e) into Equation (1) below:

$$X(i:e)=(Z_i \times D_{e4}) / (Z_e \times D_{i4}) \quad (1)$$

7. (Original) A continuously manufacturing process according to claim 6, wherein the X(i:e) is 10 or greater.

8. (Currently amended) A continuously manufacturing process according to ~~claim 6 or 7~~claim 6, wherein the Y(i) value is from 200 to 2,000, the value being calculated by substituting the pressure loss ratio Z(i), the mixer length L(i) and the inside diameter D(i) of SM(i) into Equation (2) below:

$$Y(i)=Z(i) \times L(i)/D(i) \quad (2)$$

9. (Original) A continuously manufacturing process according to claim 8, wherein the Y(i) is from 500 to 1,000.

10. (Original) A continuously manufacturing process according to any of claims 6 to 9, wherein a static mixer (SM(m)) for use in the intermediate stage of reaction is optionally placed, between the SM (i) and the SM (e).

11. (Currently amended) A continuously manufacturing process according to any of ~~claims 6 to 10~~claims 6 to 9, wherein one or more or all of the SM(i), the SM(m) placed as required, and the SM(e) comprise a plurality of static mixers.

12. (Currently amended) A continuously manufacturing process according to any of ~~claims 6 to 11~~claims 6 to 9, wherein for static mixers [SM(r), (r=1 to n)] to the total of n pieces, constituting the SM (i), the SM(m) optionally placed, and the SM(e) the total value of $\sum Y_r$ calculated using Equation (2) [i.e. $\sum Y_r = \sum Z_r \times L_r / D_r$, (the range of \sum being r=1 to n)] is 5,000 or less.

13. (Currently amended) A continuously manufacturing process according to any of ~~claims 6 to 12~~claims 6 to 9, wherein the polymer (A) is a crystalline aromatic polyester.

14. (Currently amended) A continuously manufacturing process according to any of ~~claims 6 or 13~~claims 6 to 9, wherein the cyclic ester (B) is a lactone.

15. (Original) A continuously manufacturing process according to claim 14, wherein the lactone is ϵ -caprolactone.